



Coates Screen

# Product Data Sheet

## 2-COMPONENT PAD PRINTING INKS TP 307-NT

### APPLICATION

For printing onto pre-treated polyolefines such as polyethylene and polypropylene, thermoplastics (ABS, acrylics), metals, duroplastics and epoxy resins.

### PROPERTIES

2-component pad printing inks TP 307-NT are glossy, show good opacity and high chemical and outdoor resistance.

### COLOUR SHADES

Printing inks by Coates Screen Inks GmbH correspond to the requirements of the respective current version of the EUPIA exclusion list. Pigments and other compounds based on antimony\*, arsenic, cadmium, chromium(VI), lead, mercury and selenium are not used.

\*see footnote in EUPIA list

### ADJUSTMENT FOR PAD PRINTING

2-component pad printing inks TP 307-NT are mixed with hardener TP 219/N prior to processing. Mixing ratio (parts by weight) should be:

4 parts ink TP 307-NT : 1 part hardener TP 219/N

Pot life is approx. 8 h.

Pad printing inks TP 307-NT are adjusted to printing consistency with 15–30% Additive A. Thinner VD 60 can be used as slow thinner, TPD as retarder.

### DRYING

After addition of hardener TP 219/N 2-component TP 307-NT inks dry chemically-physically within approx. 15 min. at room temperature (20- 25°C; 68- 77°F) Heat application and air circulation will reduce drying time to approx. 30 seconds.

At room temperature TP 307-NT inks are fully cured after approx. 5- 6 days.

### CLEANING

For cleaning of stencils and tools our thinner VD 40 or Cliché Spray are suitable.

### PACKING

Pad printing inks TP 307-NT are available in 1 liter containers.

### SHELF LIFE

For information regarding shelf life please see tin label.

### CLASSIFICATION

Read material safety data sheet prior to processing. The material safety data sheet according to Regulation (EC) No. 1907/2006 (REACH) contains classification according to Regulation (EC) No. 1272/2008 (CLP/GHS) as well as instructions for precautions when processing, handling and storing as well as first aid.

### STANDARD SHADES

citric yellow	TP 307/10-NT	light blue, highly opaque	TP 307/30-HD-NT
citric yellow, highly opaque	TP 307/10-HD-NT	medium blue	TP 307/31-NT
medium yellow	TP 307/11-NT	ultra marine	TP 307/32-NT
medium yellow, highly opaque	TP 307/11-HD-NT	dark blue	TP 307/33-NT
dark yellow	TP 307/12-NT	turquoise	TP 307/34-NT
dark yellow, highly opaque	TP 307/12-HD-NT	violet	TP 307/37-NT
orange	TP 307/15-NT	violet, highly opaque	TP 307/37-HD-NT
orange, highly opaque	TP 307/15-HD-NT	light green	TP 307/40-NT
ochre yellow	TP 307/17-NT	light green, highly opaque	TP 307/40-HD-NT
light red	TP 307/20-NT	fir green	TP 307/41-NT
light red, highly opaque	TP 307/20-HD-NT	brilliant green	TP 307/42-NT
red bright	TP 307/21-NT	light brown	TP 307/50-NT
red bright, highly opaque	TP 307/21-HD-NT	dark brown	TP 307/51-NT
carmine red	TP 307/22-NT	white	TP 307/60-NT
carmine red, highly opaque	TP 307/22-HD-NT	white, highly opaque	TP 307/60-HD-NT
pink	TP 307/25-NT	black	TP 307/65-NT
light blue	TP 307/30-NT	black, highly opaque	TP 307/65-HD-NT

Other shades can be manufactured subject to our special shade regulation.

### PROCESS COLOURS ACCORDING TO EUROPE SCALE

yellow	TP 307/180-NT
magenta	TP 307/181-NT
cyan	TP 307/182-NT

### C-MIX 2000 BASE COLOURS

primrose	TP 307/Y30	violet	TP 307/V50
golden yellow	TP 307/Y50	blue	TP 307/B50
orange	TP 307/O50	green	TP 307/G50
scarlet	TP 307/R20	black	TP 307/N50
red	TP 307/R50	white	TP 307/W50
magenta	TP 307/M50	varnish	TP 307/E50

*The statements in our product and safety data sheets are based on our present experiences, however they are no assurance of product properties and do not justify a contractual legal relationship. They serve to advise our business associates, but it is absolutely necessary to make your own printing tests under local conditions, with regard to the intended purpose prior to starting the job. - All former product data sheets are no longer valid. MAY 2015 – VERSION No. 6*

**Coates Screen Inks GmbH**  
**Wiederholdplatz 1 90451 Nürnberg**  
**Phone: 0911 6422 0 Fax: 0911 6422 200**  
<http://www.coates.de>