

Product Data Sheet

Screen Printing Ink

SunChemical[®]
Coates Screen Inks

HG

Solvent Based Screen Ink Range, 1-Component

APPLICATION

Screen printing inks for printing on thermoplastics, especially rigid and plasticized PVC, PMMA (acrylic glass) polycarbonate, print treated polyester foils, various types of polystyrene, ABS, SAN and copolymers.

PROPERTIES

- Screen inks HG are solvent based, 1-component screen printing inks with a good printability. They dry quickly by evaporation of solvents and result in a glossy to satin gloss finish.
- HG inks show good weather resistance.
- Flexibility of these inks is good. Decorative prints with HG can be applied to pre-treated (usually with primer) polyester foils used for membrane switch overlays.
- HG prints show good thermal forming properties (deep drawing applications).
- Adjusted with quickly evaporating thinners, e.g. VD 40, HG/VSP, HG inks can also be used for roller or spray coating applications.
- Note: As thermoplastic injection moulds especially PS, PC and PMMA are sensitive to tension cracks pre-tests are absolutely essential for such printing applications.

COLOUR SHADES - OVERVIEW

- Mixing System: C-MIX 2000 12 colour shades for mixing of RAL, PMS and HKS colours.
C-MIX 2000-XL 5 extra highly lightfast and weather resistant colour shades.
- Opaque: Standard Colour shades with medium to good opacity.
Standard HD Highly opaque colour shades.
- Transparent: "480" colours Highly transparent colour shades.
- Process Inks: "180" colours 4 transparent colour shades according to ISO 2846-4.
- Bronzes: B / AB / MG Gold, silver and copper shades.
- Special colour shades are available upon request.
- More information about available colour shades in the detailed tables in section Colour Shades.

CHOICE OF PIGMENTS AND LIGHT FASTNESS

Colour shades of HG ink range contain pigments with a high light fastness. Light fastness and weather resistance will reduce if thinner layers are applied or if base colours are mixed with a high ratio of white or varnish. For high light fastness and weather resistance requirements, we offer 5 colour shades C-MIX 2000-XL (2 yellow / 2 red / 1 white).

Applied on suitable substrates screen printing inks HG are suitable for outdoor applications.

ADJUSTMENT FOR SCREEN PRINTING

- Screen printing inks HG are not supplied in a ready-to-print adjustment.
- Depending on local conditions the ink is adjusted for printing by addition of 15 to 25 % by weight thinner or retarder (stir with mixer, agitator).
- Prior to printing, the inks should be stirred well to obtain a homogeneous dispersion of all ingredients.

THINNERS / RETARDERS

For adjustment of screen inks HG, the following products are available:

Thinner:	<input type="radio"/> VD 20	Very quick thinner, good solving power
	<input type="radio"/> VD 40	Quick, very high solving power
	<input checked="" type="checkbox"/> VD 50	Standard thinner
	<input checked="" type="checkbox"/> VD 60	Standard thinner (mild odour)
	<input type="radio"/> XVH	Very mild thinner, low solving power
Retarder:	<input checked="" type="checkbox"/> VZ 10	Quick retarder
	<input type="radio"/> VZ 20	Medium retarder
	<input checked="" type="checkbox"/> VZ 25	Medium retarder
	<input type="radio"/> VZ 30	Very slow retarder
	<input type="radio"/> VZ 40	Very slow retarder

■= Preferred ○= Suitable

Depending on printing conditions, the products listed above can be mixed into the inks individually or as mixtures. Please note that depending on evaporation rate of the thinner/retarder used drying times may be longer.

Thinner/retarder should be mixed into the ink thoroughly using a mixer or agitator. In addition, inks should be stirred well prior to each processing to obtain a homogeneous dispersion of all ingredients.

ADJUSTMENT FOR SPRAY COATING APPLICATION

HG inks can also be roller coated or applied with a spray gun. For these applications, HG inks are thinned with quick evaporating thinners such as VD 20 or VD 40 (preferred for roller coating) or HG/VSP (spray coating). Addition of thinner, usually >50%, depends on the required processing viscosity.

ADDITIONAL AUXILIARY AGENTS

Application	Product	Addition in % by weight	Additional Information
Retarder paste	VP/K	Max. 10%	Possibly slightly reduced gloss
	LAB-N 111420/VP	Max. 10%	Gloss slightly reduced
Viscosity increase	Thickening powder	Max. 3%	Stir with mixer
Matting	Matting powder	Max. 5%	Stir with mixer
Flow agent	VM 2	0.3 - 0.5%	Do not overdose!
Anti floating agent	LAB-N 561248	1 - 1.5%	Stir with mixer

OVERPRINTING

Generally, it is not necessary to overprint HG inks with varnish. However, overprinting to increase chemical resistances is possible with the following solvent based special varnishes:

- HG/E50: 1-component, Standard varnish of C-MIX colour range
- SG 70/15: 1-component, Increase of alcohol and petrol resistance
- PK 70/36: 1-component, Increase of alcohol and petrol resistance
- Z 70/114-PVC: 2-component, for PVC substrates, high solvent resistance
- Note: Pre-tests to determine suitability are essential!

BRONZE COLOURS, MIXING OF BRONZE INKS

Bronze colours 75/AB to 79/AB and metal gloss colours 75/MG to 79/MG are available.

Printers can mix bronzes themselves using bronze pastes B 75, B 76, B 77 and B 79 as well as bronze powder B 78-POWDER. For examples of colour shades please refer to our Bronze Colour Card.

These "B" bronze pastes and "B" bronze powder are mixed with bronze binder HG/B or varnish HG/E50 prior to processing.

Mixing ratios in parts by weight:

Gold bronze paste/powder	to	HG/B or HG/E50	= 1 : 3 - 4
Silver bronze paste	to	HG/B or HG/E50	= 1 : 4 - 5

Contrary to AB and MG, bronze colours B bronzes are prone to oxidation (exception B 78-POWDER). Therefore, they should be overprinted, e.g. with HG/E50. B-bronzes are not recommended for long-term outdoor applications.

B 78-POWDER does not tend to oxidation. The pale copper shade will not darken with time. Colour of inks mixed with B 78-POWDER is similar to colour 78/AB as shown on our "bronze colour card".

Note: When overprinting bronze colours (B/ AB/ MG) with varnish or other colour shades, it is essential to carry out pre-tests to check intermediate adhesion of the ink layers (fingernail test, tape test).

DRYING

HG screen printing inks dry physically, i.e. by evaporation of solvents.

Drying times below are only approximate as drying properties depend on various factors:

- Type and amount of thinners/retarders used.
- Thickness of printed ink layer; number of overprinted ink layers.
- Rack drying or tunnel dryer.
- Temperature, air supply, speed of air stream.
- Type of substrate/material printed.

Depending on local conditions, drying time in a drying frame (rack) is approx. 10 - 15 minutes at room temperature (20°C). Drying time using an efficient tunnel dryer (e.g. 2 hot air and 1 cold air section) is about 20 - 60 seconds at a temperature of 50°C.

Note: Addition of retarders may result in much longer drying times!

SCREEN FABRIC / STENCILS

HG inks have been formulated for printing with fabrics ranging from 77 to 140 threads/cm. Suitability for printing with coarser or finer fabrics should be determined by corresponding pre-trials.

All copy emulsions and capillary films suitable for solvent based screen inks can be used, such as our program of SunCoat or Murakami products.

CLEANING

Stencils and tools can be cleaned with our universal cleaning agents URS or URS 3.

PACK SIZE

Screen printing inks HG are delivered in 1 litre containers. Other pack sizes are available upon request.

SHELF LIFE

In closed original containers, HG inks generally have a shelf life of 5 years from date of production.

For exact date of expiry, please refer to the label.

SAFETY DATA SHEETS

Read safety data sheet prior to processing

Safety data sheets comply with Regulation (EC) No. 1907/2006 (REACH), Appendix II.

CLASSIFICATION AND LABELLING

Hazard classification and labelling comply with Regulation (EC) No. 1272/2008 (CLP/GHS).

CONFORMITY

Coates Screen Inks GmbH does not use any of the substances or mixtures for the production of printing inks, which are banned according to the EUPIA (European Association of the Printing Inks Industry) exclusion policy. Screen printing inks range HG C-MIX 2000 colour shades, standard, highly opaque standard colours (HD), process colours, silver, fluorescent colours and transparent colours comply with the requirements of toy standard „EN 71-3:2019 Safety of toys – Migration of certain elements (category III: scraped off material).

Further compliance confirmations are available upon request.

ADDITIONAL INFORMATION ABOUT OUR PRODUCTS

Product data sheets: Auxiliary Agents for Screen Printing HM

Brochures: Solvent Based Screen Printing Inks

Internet: Various technical articles are available for download on www.coates.de, section "SN-Online"

FOR COLOUR RANGES, PLEASE REFER TO NEXT PAGE.

COLOUR SHADES

C-MIX 2000 BASE COLOUR SHADES					
Mixing system for matching of PMS, HKS, RAL colours (on white substrates) Start formulations available in data base „Formula Management C-MIX 2000“ According to colour card C-MIX 2000					
primrose	HG/Y30	red	HG/R50	green	HG/G50
golden yellow	HG/Y50	magenta	HG/M50	black	HG/N50
orange	HG/O50	violet	HG/V50	white	HG/W50
scarlet	HG/R20	blue	HG/B50	varnish	HG/E50
C-MIX 2000 BASE COLOUR SHADES XL					
(extremely lightfast pigmentation for yellow / red and white)					
primrose	HG/Y30-XL	scarlet	HG/R20-XL	white	HG/W50-XL
golden yellow	HG/Y50-XL	red	HG/R50-XL		
STANDARD Colour Range (medium opacity)					
According to colour card STANDARD 1 for screen printing inks Availability of further standard shades upon request					
citric yellow	HG 10/NT-NEU	dark pink	HG 24/NT-NEU	fir green	HG 41/NT-NEU
medium yellow	HG 11/NT-NEU	light blue	HG 30/NT-NEU	brilliant green	HG 42/NT-NEU
dark yellow	HG 12/NT-NEU	medium blue	HG 31/NT-NEU	reseda green	HG 43/NT-NEU
light orange	HG 14/NT-NEU	ultra marine	HG 32/NT-NEU	grass green	HG 44/NT-NEU
orange	HG 15/NT-NEU	dark blue	HG 33/NT-NEU	light brown	HG 50/NT-NEU
ochre yellow	HG 17/NT-NEU	turquoise	HG 34/NT-NEU	dark brown	HG 51/NT-NEU
light red	HG 20/NT-NEU	marine blue	HG 35/NT-NEU	white	HG 60/NT-NEU
bright red	HG 21/NT-NEU	violet	HG 36/NT-NEU	black	HG 65/NT-NEU
carmine red	HG 22/NT-NEU	light green	HG 40/NT-NEU		
STANDARD Colour Range HD (high opacity)					
According to colour card STANDARD HD for screen printing inks Availability of further standard HD shades upon request					
citric yellow, highly opaque	HG 10/HD-NT-NEU	bright red, highly opaque	HG 21/HD-NT-NEU		
medium yellow, highly opaque	HG 11/HD-NT-NEU	carmine red, highly opaque	HG 22/HD-NT-NEU		
dark yellow, highly opaque	HG 12/HD-NT-NEU	white, highly opaque	HG 60/HD-NT-NEU		
orange, highly opaque	HG 15/HD-NT-NEU	black, highly opaque	HG 65/HD-NT-NEU		
light red, highly opaque	HG 20/HD-NT-NEU				
SPECIAL PRODUCTS: Special Colour Shades, Varnishes, Pastes					
Information about availability upon request					
black, matt	HG 65/MT-NT-NEU	black light varnish „blueish“	HG 70/66-NT		
black toning paste	HG 65/22	black light varnish “yellowish”	HG 70/84-NT		
black, IR-permeable	HG 66/IR	overprint varnish	HG/E50		
blackboard black	HG 67	overprint varnish, matt	HG 70/MT		
black, low PAH content	HG 68/NT	varnish, highly transparent	HG 70/20		
transparent paste	HG/TP	UV-absorbing varnish	HG 70/96-NT		
etch imitation	HG 63/00	obliterating grey	HG 74		
matt paste	HG/MP	phosphorescent ink	HG 96		
bronze binder	HG/B				

Matching of PMS, RAL, NCS colours and special shades upon request.

FOR FURTHER COLOUR RANGES, PLEASE REFER TO NEXT PAGE.

COLOUR SHADES

4 COLOUR PROCESS INKS (CMYK) According to colour card STANDARD 1 for screen printing inks			
process yellow	HG 180/NT-NEU	process black	HG 65/NT-NEU
process magenta	HG 181/NT-NEU	transparent paste	HG/TP
process cyan	HG 182/NT-NEU		
Highly Transparent Inks „480 Range“ According to colour Card HG Transparent Inks			
highly transparent yellow	HG 480/NT-NEU	highly transparent dark blue	HG 482/00-NT
highly transparent magenta	HG 481/NT-NEU	highly transparent violet	HG 483/NT-NEU
highly transparent red	HG 481/00-NT	highly transparent green	HG 484/NT-NEU
highly transparent light blue	HG 482/NT-NEU	highly transparent orange	HG 485/NT-NEU
AB – BRONZE INKS and MG – METAL GLOSS INKS According to Bronze Colour Card			
AB Bronze Inks		MG Metal Gloss Inks	
rich gold	HG 75/AB	rich gold	HG 75/MG
rich pale gold	HG 76/AB	rich pale gold	HG 76/MG
pale gold	HG 77/AB	pale gold	HG 77/MG
copper	HG 78/AB	copper	HG 78/MG
silver	HG 79/AB	silver	HG 79/MG

Matching of PMS, RAL, NCS colours and special shades upon request.

All above information refers to the colour shades listed in this product data sheet and other standard shades of this screen ink range. Information about availability of further standard shades upon request.

In some individual cases the product characteristics of special colour shades and modifications of this ink type manufactured upon customer request may differ from the above properties.

The statements in our product and safety data sheets are based on our present experiences, however they are no assurance of product properties and do not justify a contractual legal relationship. We provide these details to inform customers about our products and their possible applications. However, on account of various factors influencing processing of our products it is absolutely essential to carry out printing trials under local production conditions. Choice of individual ink types and their suitability for the intended application is the sole and entire responsibility of the user. We do not assume any liability for any problems of technical or process-related nature. Any liability shall be limited to the value of the goods delivered by us and processed by the user.

All former product data sheets are no longer valid.

January 2021 - Version B4

Coates Screen Inks GmbH
 Wiederholdplatz 1 90451 Nürnberg
 Tel.: 0911 6422 0 Fax: 0911 6422 200
<http://www.coates.de>