

Product Data Sheet

Pad Printing Ink

SunChemical[®]
Coates Screen Inks

TP 273 & TP 273/T

Solvent Based Pad Printing Ink Range, 1- and (alternatively) 2-Component

APPLICATION

Pad printing ink ranges TP 273 and TP 273/T are applied on demanding substrates such as polyamide (PA), polyurethane (PU), thermoplastic elastomers (TPE, TPU, TPS etc.), so-called soft touch coatings as well as on rubber, leather and synthetic leather.

For printing on thermoplastic elastomers ink range TP 273/T is especially suitable.

PROPERTIES

- Pad inks TP 273 and TP 273/T are solvent based pad printing inks. They can be processed as 1-component and (alternatively) as 2-component ink with hardener.
- Processed as 1-component ink TP 273 and TP 273/T dry physically, as 2-component ink physically chemically-reactive. They result in a satin gloss finish.
- TP 273/T is a modification of TP 273. Depending on printing conditions and type of substrate, in some individual applications TP 273/T shows better printability and adhesion.
- For printing on thermoplastic elastomers ink range TP 273/T is especially suitable.
- TP 273 and TP 273/T prints show a high elasticity and flexibility.
- Until further notice, both systems are available.
- Processing as 2-component ink will further increase ink adhesion properties on difficult substrates. 2-component processing is especially recommended for thermoplastic elastomers.
- TP 273 and TP 273/T inks are suitable for medium-term outdoor applications.
- Note: Because of the variety of substrates, pre-tests are essential. It is also advised to check efficiency of possibly required pre-treatment of substrates (cleaning/degreasing, flame/corona/plasma treatment) or maybe even post-treatment (flame-drying).

COLOUR SHADES - OVERVIEW

- Mixing System: C-MIX 2000 12 colour shades for mixing of RAL, PMS and HKS colours.
- Opaque: Standard Colour shades with medium to good opacity.
Standard HD Highly opaque colour shades.
- Special colour shades are available upon request.
- More information about available colour shades in the detailed tables in section Colour Shades.

CHOICE OF PIGMENTS AND LIGHT FASTNESS

Colour shades of TP 273 and TP 273/T ink ranges contain pigments with a high light fastness. Light fastness and weather resistance will reduce if thinner layers are applied or if base colours are mixed with a high ratio of white or varnish.

Applied on suitable substrates pad printing inks TP 273 and TP 273/T are suitable for medium-term outdoor applications.

ADJUSTMENT FOR PAD PRINTING

- Pad printing inks TP 273 and TP 273/T are not supplied in a ready-to-print adjustment.
- **Processed as 1-component ink (without addition of hardener):**
Ink is adjusted to printing consistency by addition of thinner or retarder (stir with mixer or agitator).

- **Processed as 2-component ink (with addition of hardener):**

As 2-component ink TP 273 and TP 273/T inks have to be mixed with hardener at a specified ratio prior to processing. Thinner is added after addition of hardener.

The mixed ink should be allowed to pre-react for approx. 15 minutes prior to processing (recommendation). Processing is then possible for a specified period of time (=pot life).

Hardener:

Alternatively, pad ink ranged TP 273 and TP 273/T can be processed as 2-component ink with **hardener TP 219** or **TP 219/N**. Hardener TP 219/N is especially recommended for printing on flexible/elastic substrates such as thermoplastic elastomers.

Hardeners are added to TP 273 or TP 273/T inks at a specified ratio.

Ink : Hardener =10 : 1 (parts by weight)

Hardeners are sensitive to humidity. Therefore, containers always have to be tightly closed.

Pot life:

- Ink mixed with hardener may only be processed within a limited period of time (=pot life)
- **Pot life of TP 273 and TP 273/T + hardener is approx. 8 h (at 20°C).**
Higher temperatures will reduce pot life.
- We do not recommend processing the inks for longer than the pot life as adhesion and resistance properties will then continually deteriorate, even if the ink still seems to be liquid and processable.

THINNERS / RETARDERS

Depending on local conditions, these inks are adjusted to printing consistency by addition of 15 – 30 % by weight of thinner or retarder.

Generally, the thinner suitable for TP 273 and TP 273/T inks is Additive A!

The additional products listed below should only be used if the required printing quality/ink transfer cannot be achieved using additive A (e.g. drying too slow or too fast).

For adjustment of pad inks TP 273 and TP 273/T, the following products are available:

Thinner:	<input type="radio"/> Additive C	Extremely quick thinner, good solving power
	<input type="radio"/> VD 40	Quick, very strong solving power
	<input type="radio"/> Additive B	Quick thinner, good solving power
	<input checked="" type="radio"/> Additive A	Standard thinner
	<input type="radio"/> Additive U	Standard thinner, free of cyclohexanone
	<input type="radio"/> VD 60	Slow thinner
Retarder:	<input type="radio"/> TPD	Very slow retarder

■= Preferred ○= If required

Note:	For printing with thick and thin steel clichés sensitive to corrosion	
	<input type="radio"/> Additive A/00	Standard thinner with anti-corrosion additive
	<input type="radio"/> Additive B/00	Quick thinner with anti-corrosion additive

Depending on printing conditions, the products listed above can be mixed into the inks individually or as mixtures. Please note that depending on evaporation rate of the thinner/retarder used drying times may be longer.

Thinner/retarder should be mixed into the ink thoroughly using a mixer or agitator. In addition, inks should be stirred well prior to each processing to obtain a homogeneous dispersion of all ingredients.

ADDITIONAL AUXILIARY AGENTS

Application	Product	Addition in % by weight	Additional Information
Antistatic paste	LAB-N 111420	Max. 10%	Possibly slightly reduced gloss
Retarder paste	LAB-N 111420/VP	Max. 10%	Possibly slightly reduced gloss
Viscosity increase	Thickening powder	Max. 3%	Stir with mixer
Matting	Matting powder	Max. 5%	Stir with mixer
Flow agent	VM 1	1 - 5%	Do not overdose!

OVERPRINTING

Generally, it is not necessary to overprint TP 273 and TP 273/T inks with varnish. However, overprinting to achieve an enhanced protection of ink layers is possible with TP 273/E50 or TP 273/T-E50.

BRONZE COLOURS

Bronze colours are available upon request.

Printers can mix bronzes themselves using bronze pastes B 75, B 76, B 77 and B 79 as well as bronze powder B 78-POWDER. For examples of colour shades please refer to our Bronze Colour Card.

These "B" bronze pastes and "B" bronze powder are mixed with bronze binder TP 273/B or varnish TP 273/E50 or TP 273/T-E50 prior to processing.

Mixing ratios in parts by weight:

Gold bronze paste/powder	to	TP 273/B or TP 273/E50 or TP 273/T-E50	= 1 : 3 - 4
Silver bronze paste	to	TP 273/B or TP 273/E50 or TP 273/T-E50	= 1 : 4 - 5

Contrary to AB and MG bronze colours, B bronzes are prone to oxidation (Exception B 78-POWDER). Therefore, they should be overprinted, e.g. with TP 273/E50 or TP 273/T-E50.

B 78-POWDER does not tend to oxidation. The pale copper shade will not darken with time. Colour of inks mixed with B 78-POWDER is similar to colour 78/AB as shown on our "bronze colour card".

Note: When overprinting bronze colours (B/ AB/ MG) with varnish or other colour shades it is essential to carry out pre-tests to check intermediate adhesion of the ink layers (fingernail test, tape test).

DRYING / HARDENER REACTION

1. **Processing WITHOUT addition of hardener:**
Ink dries physically, i.e. by evaporation of solvents.
2. **Processing WITH addition of hardener TP 219 or TP 219/N:**
First, ink dries physically, followed by chemical cross-linkage reaction.
Drying and reaction temperature of hardener must be at least 15°C when using TP 219 and 20°C using TP 219/N!

Drying

Drying times below are only approximate as drying properties depend on various factors:

- Type and amount of thinners/retarders used.
- Thickness of printed ink layer (single print, multi-layer print).
- Drying temperature.

Depending on local conditions, average drying time is approx. 2 – 3 minutes. Drying time with heat application (e.g. hot air fan) and air circulation is about 30 - 60 seconds.

Complete drying may take several hours, also depending on the substrate.

Hardener Reaction

Basically, the increased resistance properties of the printed ink film are only achieved after complete drying followed by chemical cross linkage reaction between ink and hardener. This cross linkage reaction depends on time and temperature.

The following are guide values only:

Temperature	Time approx.	Condition of ink	Additional information
<15°C air drying		Hardener TP 219 does not react!	Ink film will not achieve any resistance
<20°C air drying		Hardener TP 219/N does not react!	Ink film will not achieve any resistance
20°C air drying	20 min.	"touch-dry"	No resistance yet
	>72 h	High degree of cross-linkage	High resistances achieved
	>5 days	Maximum degree of cross-linkage	Maximum resistances achieved
80°C oven curing	approx. 5 min.	Dry enough for overprinting	No resistance yet
	60 min.	High degree of cross-linkage	High resistance values achieved

Resistance Tests

Resistances should not be checked before the ink has fully cured/cross-linked:
Drying with 20°C/>72h; with 80°C/>60 minutes.

CLICHÉ

All commercial types of clichés (polymer, thin and thick steel, ceramic) are suitable for processing TP 273 and TP 273/T inks.

Note: Standard shades 17, 50 and 51 cannot be used for closed ink systems with a magnet holder as they contain pigments with iron oxide content.

CLEANING

The longer inks dry on clichés, pots and tools the harder will be their removal due to the chemical cross-linkage reaction. Therefore, always remove ink residues as soon as possible using our universal cleaning agents URS, URS 3 or thinner VD 40.

PACK SIZE

Pad printing inks TP 273 and TP 273/T are delivered in 1 litre containers. Other pack sizes are available upon request.

SHELF LIFE

In closed original containers, TP 273 and TP 273/T inks generally have a shelf life of 3 years from date of production. Hardeners TP 219 and TP 219/N have a shelf life of 14 months from date of production, also in closed original containers.

For exact date of expiry, please refer to the label.

SAFETY DATA SHEETS

Read safety data sheet prior to processing

Safety data sheets comply with Regulation (EC) No. 1907/2006 (REACH), Appendix II.

CLASSIFICATION AND LABELLING

Hazard classification and labelling comply with Regulation (EC) No. 1272/2008 (CLP/GHS).

CONFORMITY

Coates Screen Inks GmbH does not use any of the substances or mixtures for the production of printing inks, which are banned according to the EUPIA (European Association of the Printing Inks Industry) exclusion policy. Pad printing inks range TP 273 and TP 273/T standard shades, C-MIX 2000 colour shades, standard, highly opaque standard colours (HD), process colours, silver and fluorescent colours comply with the requirements of toy standard „EN 71-3:2019 Safety of toys – Migration of certain elements (category III: scraped off material). Further compliance confirmations are available upon request.

ADDITIONAL INFORMATION ABOUT OUR PRODUCTS

Product data sheets: Auxiliary Agents for Pad Printing HM

Brochures: Pad Printing Inks

Internet: Various technical articles are available for download on www.coates.de, section “SN-Online”; e.g. “Processing of 2-component Inks”

FOR COLOUR RANGES, PLEASE REFER TO NEXT PAGE.

COLOUR SHADES

C-MIX 2000 BASE COLOUR SHADES					
Mixing system for matching of PMS, HKS, RAL colours (on white substrates)					
Start formulations available in data base „Formula Management C-MIX 2000“					
According to colour card C-MIX 2000					
primrose	TP 273/Y30 <i>TP 273/T-Y30</i>	red	TP 273/R50 <i>TP 273/T-R50</i>	green	TP 273/G50 <i>TP 273/T-G50</i>
golden yellow	TP 273/Y50 <i>TP 273/T-Y50</i>	magenta	TP 273/M50 <i>TP 273/T-M50</i>	black	TP 273/N50 <i>TP 273/T-N50</i>
orange	TP 273/O50 <i>TP 273/T-O50</i>	violet	TP 273/V50 <i>TP 273/T-V50</i>	white	TP 273/W50 <i>TP 273/T-W50</i>
scarlet	TP 273/R20 <i>TP 273/T-R20</i>	blue	TP 273/B50 <i>TP 273/T-B50</i>	varnish	TP 273/E50 <i>TP 273/T-E50</i>
STANDARD (medium opacity)					
According to colour card STANDARD 1 for pad printing inks or TP 247/ TP 249...					
Availability of further standard shades upon request					
citric yellow	TP 273/10-NT <i>TP 273/T-10-NT</i>	pink	TP 273/25-NT <i>TP 273/T-25-NT</i>	light green	TP 273/40-NT <i>TP 273/T-40-NT</i>
medium yellow	TP 273/11-NT <i>TP 273/T-11-NT</i>	light blue	TP 273/30-NT <i>TP 273/T-30-NT</i>	white	TP 273/60-NT <i>TP 273/T-60-NT</i>
light red	TP 273/20-NT <i>TP 273/T-20-NT</i>	medium blue	TP 273/31-NT <i>TP 273/T-31-NT</i>	black	TP 273/65-NT <i>TP 273/T-65-NT</i>
bright red	TP 273/21-NT <i>TP 273/T-21-NT</i>	ultra marine	TP 273/32-NT <i>TP 273/T-32-NT</i>		
carmine red	TP 273/22-NT <i>TP 273/T-22-NT</i>	dark blue	TP 273/33-NT <i>TP 273/T-33-NT</i>		
STANDARD Colour Range HD (high opacity)					
According to colour card STANDARD HD for pad printing inks					
Availability of further standard HD shades upon request					
white, highly opaque	TP 273/60-HD-NT <i>TP 273/T-60-HD-NT</i>	black, highly opaque	TP 273/65-HD-NT <i>TP 273/T-65-HD-NT</i>		
SPECIAL PRODUCTS: Special Colour Shades, Varnishes, Pastes					
Information about availability upon request					
black, low-grade PAH	TP 273/68-NT <i>TP 273/T-68-NT</i>	bronze binder	TP 273/B	transparent paste	TP 273/TP
4 COLOUR PROCESS INKS (CMYK)					
According to colour card STANDARD 1 for pad printing inks or TP 247/ TP 249...					
Upon request					
AB – BRONZE INKS and MG – METAL GLOSS INKS					
According to Bronze Colour Card					
AB Bronze Inks Upon request			MG Metal Gloss Inks Upon request		

Matching of PMS, RAL, NCS colours and special shades upon request.

All above information refers to the colour shades listed in this product data sheet and other standard shades of this pad printing ink range. Information about availability of further standard shades upon request.

In some individual cases the product characteristics of special colour shades and modifications of this ink type manufactured upon customer request may differ from the above properties.

The statements in our product and safety data sheets are based on our present experiences, however they are no assurance of product properties and do not justify a contractual legal relationship. We provide these details to inform customers about our products and their possible applications. However, on account of various factors influencing processing of our products it is absolutely essential to carry out printing trials under local production conditions. Choice of individual ink types and their suitability for the intended application is the sole and entire responsibility of the user. We do not assume any liability for any problems of technical or process-related nature. Any liability shall be limited to the value of the goods delivered by us and processed by the user.

All former product data sheets are no longer valid.

January 2021 - Version B4

Coates Screen Inks GmbH
Wiederholdplatz 1 90451 Nürnberg
Tel.: 0911 6422 0 Fax: 0911 6422 200
<http://www.coates.de>